



"The Go To Guys For Metal"

STANDARD COLORS: 70% PVDF resin based coatings provide high-performance durability for exterior and interior applications. These coatings are designed to resist fading, chalking, and abrasion. Meets the requirement of AAMA 2605-13 and AAMA 620-02.




Regal White ▲ ●




Terra Cotta ▲




Colonial Red ▲ ●



Burgundy ▲ ●




Slate Blue ▲




Patina Green ▲




Forest Green ▲ ●




Hartford Green ▲ ●




Charcoal Gray ▲ ●




Slate Gray ▲ ●




Dove Gray ▲




Sandstone ▲ ●




Sierra Tan ▲




Medium Bronze ▲




Dark Bronze ▲ ●



Mansard Brown ▲ ●




Matte Black ▲ ●




Acrylic Coated Mill
Finish Galvalume ▲


Premium Colors



Brilliance ▲ ★



Deep Blue Sea ▲ ★



Aged Copper ▲ ★

Key:

▲ = Available in 24 ga.


★ = Premium Color

● = Available in 29 ga. Quick
Snap 16®


Metallic Colors



Metallic Copper ▲ ★



Bright Silver ▲ ★



Champagne ▲ ★

Contact ASP for your
local distributor:

518-381-6144

SpectraLume® High Performance Metal Roofing Finishes

For Galvalume® and Aluminum Coils and Sheets

Property	Result-Steel	Test-Designation
60° Specular Gloss	25-40	ASTM D 523
Pencil Hardness	HB-2H	ASTM D 3363 NCCA 11-12
Flexibility: T Bend Mandrel	2-T(1) No Cracking	ASTM D 4145, (NCCA 11-19) No cracking or tape removal of film ASTM D 522 180 bend around 1/8" mandrel
Adhesion: Impact Reverse Impact	Acceptable (2) Acceptable (2)	ASTM D 3359, (NCCA 11-15) ASTM D 2794, (NCCA 11-6)
Abrasion: Falling Sand Transit	50 liters minimum No disfigurement	ASTM D 968 Method A
Acid Pollutants	No effect No effect <5 u. color change Hunter ΔE units	ASTM D 1308, Proc. 6.2 10% Muriatic acid, 15 min. ASTM D 1308, Proc. 6.2 20% sulfuric acid, 18 hours AAMA 2605, TEST # 7.7.3.3 70% nitric acid vapors, 30 min.
Acid Rain Test	10 cycles minimum No objectionable color change	KESTERNICH Sulfur dioxide cyclic test
Accelerated Tests		
Weatherometer, 3000 hrs. exposure	Acceptable (3)	ASTM D 822, G 155 Weatherometer
Dew Cycle Weatherometer, 500 hours exposure	Acceptable (3)	ASTM D 3361
Humidity 100% relative humidity @ 95°F	Passes 1500 hrs. (4)	ASTM D 2247
Salt Spray, 5% sat fog @ 95°F	Passes 3000 hrs. (5)	ASTM B 117 (NCCA 11-2)
Cyclic Salt fog /UV Exposure Test	Passes 2016 hrs. (6)	ASTM D 5894

Notes:

- (1) Flexible to point of metal rupture without rupture of coating.
- (2) No loss of adhesion between coating and substrate to point of metal rupture with 1/16" cross-hatch scribe pattern through coating to bare metal.
- (3) No objectionable chalking, color change or blistering.
- (4) No No. 8 size blisters.

(5) Aluminum: none or few No.8 size blisters, not more than 1/16" avg. creep or tape off scribe.

(6) No blistering and no rating less than 5 per ASTM D 714; no rusting per ASTM D 610; Rating of 6, less than 1.5 mm creepage from scribe per ASTM D 1654.

SUBSTRATES

High performance metal roofing coils are available in Galvalume®. All metal coils are structural quality and tension leveled for superior flatness. Aluminum is available in minimum quantities.

Galvalume® is a registered trademark of BIEC International, Inc.

SpectraLume®

STOCK COLORS: 70% PDVF resin based coatings are designed to resist fading, chalking and abrasion.

Architectural Sheetmetal Products offers a mill finished Galvalume® with a two-sided, clear chromate/acrylic finish that simultaneously aids roll forming without the use of lubricants and practically eliminates unsightly hand prints or stains resulting from handling and storage. The acrylic finish dissolves naturally over a period of time, and when left as is, allows for natural and even weathering.

WARRANTY

70% PVDF resin based coating finish carries a 30-year non-prorated limited warranty against fading and chalking. ASP coated materials are non-staining and virtually maintenance free. Any surface residue is easily removed with conventional cleaning solutions or detergents.

A 25-year non-prorated base metal warranty is offered for Galvalume®.

ADDITIONAL SERVICES

- Cut-to-length sheets with strippable protection
- Custom coil processing
- Aluminum available in limited colors and minimum quantities



**ARCHITECTURAL
SHEETMETAL PRODUCTS**

Architectural Sheetmetal Products, Inc.
1329 Amsterdam Road • Scotia, NY 12302

Contact ASP for your local distributor:

518-381-6144

www.aspmetals.com ©ASP, INC. 2022